

The Methodologies Adopted To Improve the Machinability in Die-Sinking EDM



P. Sreeraj, S. Thirumalai Kumaran, M. Uthayakumar, S. Suresh Kumar

Abstract: *Electrical discharge machining (EDM) is one of the oldest nontraditional machining processes, commonly used in automotive, aerospace and ship building industries for machining metals that have high hardness, strength and to make complicated shapes that cannot be produced by traditional machining techniques. The process is based on the thermoelectric energy between the work piece and an electrode. EDM is slow compared to conventional machining, low material removal rate, high surface roughness, high tool wear and formation of recast layer are the main disadvantages of the process. Tool wear rate, material removal rate and surface quality are important performance measures in electric discharge machining process. Numbers of ways are explored by researchers for improving and optimizing the output responses of EDM process. The paper summarizes the research on die-sinking EDM relating to the improvements in the output response.*

Keywords: *electrical discharge machining, conductive materials, electrode.*

I. INTRODUCTION

The use of ceramic materials has increased considerably in this century because of their special thermodynamic, mechanical, lightweight, electrical, optical, chemical and biological properties as compared to conventional metal matrixes. Reason for ceramic materials wide usage in current century applications are good chemical resistance, extra hardness and sufficient mechanical strength at high temperatures. It is proved that any material that can provide high electrical conductivity of can be machined by EDM. To machine ceramics, it is to be made conductive.

II. LITERATURE REVIEW

This study is performed on LMV JV 55 Vertical milling machine. Three The solid carbide, diamond coated, dual helix tool shown in Figure. 1 has been used for machining. The tool

has geometric parameters of 6mm of diameter, 40° of helix angle shown in Figure. 1 has been used for machining. The tool has geometric parameters of 6mm of diameter, 40° of helix angle and 6 flute are shown in Fig. xx. Working table of EDM machine was altered by Chen et al. [1] for devising an advanced mechanism for cutting pipe with rotary electrode. Increased material removal rate and reduction in tool erosion observed because of this alteration. An inversion model based on least squares theory was proposed by Sanchez et al. [2] for solving machining of AISI 1045 steel with a set of response parameters. Analysis of results showed that this model can be used in future applications in EDM machining. Shen et al. [3] used tubular graphite electrode with pressurized air as dielectric in their experiment for studying machining of AISI 304. In this process they noticed high material removal rate occurred. Torres et al. [4] used electrolytic copper electrodes for ED machining TiB₂ composites which is a sintered ceramic material. Because of high hardness, good wear resistance and excellent elastic properties TiB₂ composites are widely used in industry. These composites can be EDM machined like other ceramic materials because of good thermal and electrical conductivity. Design of experiments used to formulate the experimental table and against normal out responses MRR, EWR and surface roughness were measured. Optimum combinations of parameters were evaluated.

Kucukturk and Coguna [5] introduced a method for machining electrically non-conductive materials by introducing a conductive layer coating over the surface to be machined. After erosion of the conductive layer in order to keep machining they added graphite powder in die electric so that machining can be done. They successfully machined Al₂O₃, ZrO₂, SiC, B₄C and glass samples with this new technique. Tang and Du [6] used tap water as die electric in machining of Ti-6Al-4V material because tap water which is good for environment, non-hazardous and available in plenty. Optimization process was carried out by combining grey relational analysis and Taguchi method and showed it can be used in other processes.

Optimization of process parameters in machining of Al-B₄C composite was done by Pares Kumar and Ravi Parkash [7]. Patel et al. [8] investigated the EDM machinability of ceramic composite material Al₂O₃-SiCw-TiC with process parameters discharge current, pulse-on time, duty cycle and gap voltage.

Using the response surface methodology, Chiang [9] investigated the performance of EDM on Al₂O₃+TiC mixed ceramic. Interaction effect of each process parameter was evaluated separately.

Manuscript published on 30 December 2019.

* Correspondence Author (s)

P. Sreeraj, Department of Automobile Engineering, Kalasalingam Academy of Research and Education, Krishnankoil-626126, India. Email: pathiyasseril@gmail.com

S. Thirumalai Kumaran*, Faculty of Mechanical Engineering, Kalasalingam Academy of Research and Education, Krishnankoil-626126, India. Email: thirumalaikumaran@yahoo.com

M. Uthayakumar, Faculty of Mechanical Engineering, Kalasalingam Academy of Research and Education, Krishnankoil-626126, India. Email: uthaykumar@gmail.com

S. Suresh Kumar, Faculty of Mechanical Engineering, Kalasalingam Academy of Research and Education, Krishnankoil-626126, India. Email: sureshme48@gmail.com

© The Authors. Published by Blue Eyes Intelligence Engineering and Sciences Publication (BEIESP). This is an [open access](https://creativecommons.org/licenses/by-nc-nd/4.0/) article under the CC-BY-NC-ND license <http://creativecommons.org/licenses/by-nc-nd/4.0/>



The Methodologies Adopted To Improve the Machinability in Die-Sinking EDM

Si₃N₄-TiN ceramic composite, which can be used in high-temperature environments, has been EDM machined by Selvarajan et al. [10] and optimized by using grey relational analysis. Result showed that considerable improvement in the process by this optimization. Rahanga and Patowaria [11] used W-Cu powder in 75%W-25%Cu composition tool material to prepare the electrode by powder. It was found that the hardness of metal increased by three times. Gill and Kumar [12] manufactured (Cu-Mn) electrode and used this for machining hot die steel (H11) by EDM process. Purpose of this research is to induce manganese and carbon into the machined surface. This process can improve the micro hardness and Surface properties of machined surface. For achieving better surface finish and high micro hardness optimum level of process parameters were found using Taguchi method.

Many researchers have been conducted in machining of ceramics and machining of non-conductive materials. This is quite new and emerging area in EDM machining [13-18]. In order to avoid hazardous fumes and non bio degradable waste Valaki and Rathod [19] used waste vegetable oil as die electric than conventional die electrics. Trials proved that it can offer cleaner and safe environments than conventional machining. Puthumana and Joshi [20] used slotted electrode in EDM process. Gas was used as die electric fluid which is supplied through the electrodes. It was shown that in this method electrode wear reduced considerably.

A rotary copper -Tungsten electrode was used by Patel et al. [21] to machine Inconel 718. Commercial grade kerosene mixed with Al₂O₃ powder was used as die electric in this machining. It was found that considerable achievement in EDM performance. A comparison of conventional EDM and cryogenic cooled EDM was made by Hui et al. [22] in order to EDM machine Ti-6Al-4V alloy material. It was proved that cryogenic cooled EDM gives better performance than conventional EDM. Afzaal Ahmed [23] conducted EDM machining to provide a ceramic coating on aluminum for improving surface characteristics as per requirement. Researcher observed that coating was archived on the surface by slow erosion of composite tool.

Multi thin tool electrodes for machining micro holes with different lateral dimensions were first proposed by Habit Sameh et al. [24] for machining different diameter holes with extremely thin electrodes. They successfully machine micro holes in SKD 11 steel with thin Tungsten electrodes. Kerosene was used as die electric in this experiment. Suleiman Abdulkareem et al. [25] conducted experiments to reduce electrode wear while machining Ti-6Al-4V alloy with copper electrode by introducing liquid nitrogen for cooling the electrodes. It was found that EW reduced considerably due to this cooling effect. Anand Prakash Dwivedi and Sounak Kumar Choudhury [26] investigated the effect of tool rotation in EDM process while machining of AISI-D3 Steel using rotating electrodes. They found that MRR increased considerably than conventional stationary electrode EDM. Machining of V groove by conventional machining methods is difficult because of less accuracy and creation of burr while machining. Song and Chu [27] developed a new method called strip EDM for machining V grooves with high dimensional accuracy. They used thin conductive strip bent around electrode guide with its corner right angled. It was found that this method produced V groove with high

dimensional accuracy.

Ultrasonic assisted EDM with gas as die electric was used with different electrodes was used to drill a hole and then Burr removal at exit region was studied by Kurniawan et al. [28]. They found that Burr removal was affected by capacitance mostly. Flano et al. [29] used thin foil with high tension for slicing SiC slicing. They proved that it can efficiently replace wire cut EDM and have distinct advantage. Oliveira et al. [30] used EDM machining for getting a suitable coating of Titanium perovskite (CaTiO₃) in ASTM B348 6AL-4V Grade 5 Ti-6Al-4V alloy by using deionized water with calcium chloride (CaCl₂) as dielectric and graphite electrode as tool. This found very useful in biomedical applications. Dewangan et al. [31] proposed a hybrid method of using grey based Fuzzy for optimizing EDM machining of AISI P20 tool steel with commercially pure copper as tool. Commercial grade oil was used as die electric and this method can successfully apply for improving surface characteristics. This process of optimization resulted improvement in efficacy of machining. With advent of stringent pollution control laws and requirement of highly accurate requirements in machining researchers are now focusing on environmental friendly dielectric and more hybrid type EDM machining. This will be the research areas in coming decades.

III. CONCLUSION

The die-sinking EDM is a promising machining process for machining engineering materials. Several researchers achieved a near-net shape pattern on the material. However, the surface roughness, heat affected zone, tool and material removal rate are still considered as an issue during machining. The proper selection of machining parameters can reduce the adverse effect and improve the machining quality. This paper consolidates the various methodologies adopted to prepare a defect free component using die-sinking EDM.

REFERENCES

1. S.L.Chen, B.H.Yan, F.Y. Huang, "Influence of kerosene and distilled water as dielectrics on the electric discharge machining characteristics of Ti-6Al-4V," *Journal of Material Processing Technology*, vol. 87, 1999, pp. 107-111.
2. Horacio T. Sánchez, Manuel Estrems, Félix Faura, "Development of an inversion model for establishing EDM input parameters to satisfy material removal rate, electrode wear ratio and surface roughness," *International Journal of Advanced Manufacturing Technology*, vol. 57, 2011, pp. 189-201.
3. Yang Shen, Yonghong Liu, Yanzhen Zhang, Hang Dong, Pengfei Sun, Xiaolong Wang, Chao Zheng, Renjie Ji, "Effects of an electrode material on a novel compound machining of Inconel 718," *Materials and Manufacturing Processes*, vol. 31, 2011, pp. 845-851.
4. A.Torres, C.J.Luis, I.Puertas, "EDM machinability and surface roughness analysis of TiB₂ using copper electrodes," *Journal of Alloys and Compounds*, vol. 690, 2017, pp. 337-347.
5. Gokhan Kucukturk, Can Coguna, "A New method for machining of electrically nonconductive work pieces using electric discharge machining technique," *Machining Science and Technology*, vol. 14, 2010, pp. 189-207.
6. Ling Tang, Y.T.Du, "Multi-objective optimization of green electrical discharge machining Ti-6Al-4V in tap water via Grey-Taguchi method," *Materials and Manufacturing Processes*, vol. 29, 2014, pp. 507-513.

7. Paras Kumar, Ravi Parkash, "Experimental investigation and optimization of EDM process parameters for machining of aluminum boron carbide (Al-B₄C) composite," *Machining Science and Technology*, vol. 20, 2016, pp. 330-348.
8. K.M.Patel, Pulak M. Pandeym, P. Venkateswara Rao, "Optimization of process parameters for multi-performance characteristics in EDM of Al₂O₃ ceramic composite," *International Journal of Advanced Manufacturing Technology*, vol. 47, 2010, pp. 1137-1147.
9. Ko-Ta Chiang, "Modeling and analysis of the effects of machining parameters on the performance characteristics in the EDM process of Al₂O₃+TiC mixed ceramic," *International Journal of Advanced Manufacturing Technology*, vol. 37, 2008, pp. 523-533.
10. L.Selvarajan, C.Sathiy Narayanan, R.JeyaPaul, "Optimization of EDM parameters on machining Si₃N₄-TiN composite for improving circularity, cylindricity and perpendicularity," *Materials and Manufacturing Processes*, vol. 31, 2016, pp. 405-412.
11. Maneswar Rahanga, Promod Kumar Patowaria, "Parametric optimization for selective surface modification in EDM using Taguchi analysis," *Materials and Manufacturing Processes*, vol. 31, 2016, pp. 422-431.
12. Amoljit Singh Gill, Sanjeev Kumar, "Surface roughness and micro hardness evaluation for EDM with Cu-Mn powder metallurgy tool," *Materials and Manufacturing Processes*, vol. 31, 2016, pp. 514-521.
13. A.Asfana, M.Y.Ali, A.R.Mohamed, Wayne N.P.Hung, "Material removal rate of zirconia in electro discharge micromachining," *Advanced Materials Research*, vol. 1115, 2015, pp. 20-23.
14. A.Muttamara, P.Janmanee, Y.Fukuzawa, "A study of micro-EDM on silicon nitride using electrode materials," *International Transaction Journal of Engineering, Management, & Applied Science & Technologies*, vol. 1, 2010, pp. 1-7.
15. R.A.Mohamed, B.Asfana, M.Y.Ali, "Investigation of recast layer of non-conductive ceramic due to micro-EDM," *Advanced Materials Research*, vol. 845, 2014, pp. 857-861.
16. A.Muttamara, Y.Fukuzawa, N.Mohri, T.Tani, "Effect of electrode material on electrical discharge machining of alumina," *Journal of Materials Processing Technology*, vol. 209, 2009, pp. 2545-2552.
17. Y.F.Chen, Y.C.Lin, S.L.Chen, L.R.Hsu, "Optimization of electro discharge machining parameters on ZrO₂ ceramic using the Taguchi method," *Journal of Engineering Manufacture*, vol. 224, 2009, pp. 195-205.
18. Y.Fukuzawa, N.Mohri, T.Tani, A.Muttamara, "Electrical discharge machining properties of noble crystals," *Journal of Materials Processing Technology*, vol. 149, 2004, pp. 393-397.
19. Janak B.Valaki, Pravin P.Rathod, "Assessment of operational feasibility of waste vegetable oil based bio-dielectric fluid for sustainable electric discharge machining (EDM)," *International Journal of Advanced Manufacturing Technology*, vol. 87, 2016, pp. 1509-1518.
20. Govindan Puthumana, Suhas S.Joshi, "Investigations into performance of dry EDM using slotted electrodes," *International Journal of Precision Engineering and Manufacturing*, vol. 12, 2011, pp. 957-963.
21. Sagar Patel, Dignesh Thesiya, Avadhoot Rajurkar, "Aluminium powder mixed rotary electric discharge machining (PMEDM) on Inconel 718," *Australian Journal of Mechanical Engineering*, vol. 16, 2018, pp. 21-30.
22. Zhiguang Hui, Zhidong Liu, Zhongli Cao, Mingbo Qiu, "Effect of cryogenic cooling of tool electrode on machining titanium alloy (Ti-6Al-4V) during EDM," *Materials and Manufacturing Processes*, vol. 31, 2016, pp. 475-482.
23. Afzaal Ahmed, "Deposition and analysis of composite coating on aluminum using Ti-B₄C powder metallurgy tools in EDM," *Materials and Manufacturing Processes*, vol. 31, 2016, pp. 467-474.
24. Habit Sameh, Akira Okada, Yoshiyuki Uno, "Improving the productivity of electrical discharge machining process by using multi-thin electrodes," *Machining Science and Technology*, vol. 17, 2013, pp. 110-128.
25. Abdulkareem, Ahsan Ali Khan, Mohamed Konneh, "Cooling effect on electrode and process parameters in EDM," *Materials and Manufacturing Processes*, vol. 25, 2010, pp. 462-466.
26. Anand Prakash Dwivedi, Sounak Kumar Choudhury, "Effect of tool rotation on MRR, TWR and surface integrity of AISI-D3 steel using rotary EDM process," *Materials and Manufacturing Processes*, vol. 31, 2016, pp. 1844-1852.
27. Ki Young Song, Chong Nam Chu, "V-grooving using a strip EDM," *International Journal of Precision Engineering and Manufacturing*, vol. 14, 2013, pp. 2061-2066.
28. Rendi Kurniawan, S.Thirumalai Kumaran, V.Arumuga Prabu, Yu Zhen, Ki Moon Park, Ye In Kwak, Md.Mofizul Islam, Tae Jo Ko, "Measurement of burr removal rate and analysis of machining parameters in ultrasonic assisted dry EDM (US-EDM) for deburring drilled holes in CFRP composite," *Measurement*, vol. 110, 2017, pp. 98-115.
29. Olatz Flano, Yonghua Zhao, Masanori Kunieda, Kohzoh Abe, "Approaches for improvement of EDM cutting performance of SiC with foil electrode," *Precision Engineering*, vol. 49, 2017, pp. 33-40.
30. A.R.F.Oliveira, W.F.Sales, A.A.Raslan, "Titanium perovskite (CaTiO₃) formation in Ti6Al4V alloy using the electrical discharge machining process for biomedical applications," *Surface and Coating Technology*, vol. 307, 2016, pp. 1011-1015.
31. Shailesh Dewangan, Soumya Gangopadhyay, Chandan Kumar Biswas, "Multi-response optimization of surface integrity characteristics of EDM process using grey-fuzzy logic-based hybrid approach," *Engineering Science and Technology, an International Journal*, vol. 18, 2015, pp. 361-368.

AUTHORS PROFILE



P. Sreeraj is a Ph.D scholar in the Department of Automobile Engineering from Kalasalingam Academy of Research and Education (KARE), India. He is currently acting as Principal in Younus College of Engineering and Technology, Kollam.



S. Thirumalai Kumaran completed his Ph.D. degree in Mechanical Engineering from Kalasalingam Academy of Research and Education (KARE), India, in 2015. After completing Ph.D., he worked as an Assistant Professor at School of Mechanical Engineering, Yeungnam University, South Korea for a period of one year. He is currently an Associate Professor at School of Automotive and Mechanical Engineering, KARE.



M. Uthayakumar completed his Doctoral work in the area of Precision Machining. He is actively working in the development of high strength light weight composites. His other areas of interest include processing of metal matrix, polymer matrix, ceramic matrix composite and its performance studies.



S. Suresh Kumar completed his Ph.D. degree in Mechanical Engineering from Kalasalingam Academy of Research and Education (KARE), India in 2016. He also completed Post-doc from Karadeniz Technical University, Turkey in 2018. Currently, he is doing his research in the area of non-traditional machining on metal matrix composites.